

## ConduWire Technical Specifications

### Polymer Jacket Physical Properties

Property	Typical Value	Unit	Test Method
Hardness (Shore A)	94		ASTM D2240
Specific Gravity	1.26		ASTM D792-20
Tensile Strength	638	psi	ASTM D638 (20"/ min)
Elongation at Break	36	%	ASTM D638 (20"/ min)
Permeability	4.2 x 10 <sup>-8</sup>	g/(s*m <sup>2</sup> *Pa)	ASTM E96 (Sheet)
Water Absorption	0.5	%	ASTM D570
Resistivity	< 20	Ω·cm	SAE Inc. Standard 114

### Coated STR Copper Wire Physical Properties

Property	Typical Value	Unit	Test Method
Concentricity	> 80	%	ASTM D3032, Section 16
Minimum Bend Radius #6 AWG #4 AWG #2 AWG 2/0 AWG	0.5 1 1 1.5	inches	SAE Inc. Standard 115
Minimum Cold Bend Radius (6° C) #6 AWG #4 AWG #2 AWG 2/0 AWG	1 1.5 1.5 2	inches	SAE Inc. Standard 115
Minimum Polymer Wall Thickness	1.8	mm	

Additional specifications and application details available as required.  
Values subject to change.

Published Date: December 2023